

ABSTRACT OF THE DISCLOSURE

The invention relates to an oxidation and corrosion resistant braze alloy consisting of (wt.-%) 10-15% Cr, 4.5-6% Al, 0.17-0.3% Y, 8-12% Co, 0-4% W, 2.5-5% Ta, 2.0-3.5% B with $\text{Cr} + \text{Al} > 15\%$, $\text{Cr}/\text{Al} \leq 3$ and $\text{Al} + \text{Ta} > 7.5\%$, remainder Nickel and unavoidable impurities and to the use of this alloy for brazing onto a Nickel based or a Cobalt based superalloy article. The braze alloy can either be used in pure form as a paste or a foil or as a blend in a blend braze paste, in a braze tape or in a pre-sintered braze sheet.

(Fig. 3)